

ATLANTIS 3



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: January 2021

PRODUCT INFORMATION

| | |
|-----------|-----------------------------|
| Packaging | Shrink wrapped & Palletised |
|-----------|-----------------------------|

TECHNICAL INFORMATION

| | |
|---------------------------------|--------------------------------------|
| Brick Dimensions (L x W x H) | 288 x 88 x 50mm |
| Size Tolerances Mean & Range | T1, R2 |
| Configuration | Perforated |
| Voids | <35% |
| Mean Compressive Strength | ≥30 N/mm ² |
| Active Soluble Salts | S2 |
| Water Absorption | ≤8% |
| Durability | F2 |
| Gross Dry Density | 1425 Kg/m ³ |
| Equivalent Thermal Conductivity | 0,44 W/mK |
| Initial Rate of Absorption | 0.5 < IW ≤ 1.5 /(m ² min) |