


BARTON LIGHT MULTI



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: April 2022

PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Reaction to fire	A1
Brick Dimensions (L x W x H)	215 x 102.5 x 65mm
Size Tolerances Mean & Range	T1, R1
Configuration	Frogged
Voids	N/A
Mean Compressive Strength	20 N/mm ²
Active Soluble Salts	S2
Water Absorption	12%
Durability	F2
Gross Dry Density	1800 kg/m ³
Equivalent Thermal Conductivity	P=90% 0.55
Initial Rate of Absorption	Min. 1.0 Max. 5.0 kg/m ²