


RED GLAZED



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: December 2024

PRODUCT INFORMATION

Packaging	Shrink wrapped, banded & Palletised
-----------	-------------------------------------

TECHNICAL INFORMATION

Reaction to fire	A1
Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R2
Configuration	Perforated
Voids	24%
Mean Compressive Strength	126 N/mm ²
Active Soluble Salts	S2
Water Absorption	2%
Durability	F2
Gross Dry Density	1700 Kg/m ³
Equivalent Thermal Conductivity	0.79 W/mK
Initial Rate of Absorption	0.2 kg/(m ² .min)