

CINDER COAL



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: January 2021

PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102.5 x 65mm
Size Tolerances Mean & Range	T1, R1
Configuration	Frogged
Voids	<20%
Mean Compressive Strength	12 N/mm ²
Active Soluble Salts	S2
Water Absorption	19%
Durability	F2
Gross Dry Density	1450Kg/m ³
Equivalent Thermal Conductivity	0,69 W/mK
Initial Rate of Absorption	1-5 kg/(m ² min)