


## CORBUSIER



[www.bespokebrick.com](http://www.bespokebrick.com)

01634 707707

[enquiries@bespokebrick.com](mailto:enquiries@bespokebrick.com)

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent, ME2 4UY

Issue Date: January 2021

## PRODUCT INFORMATION

|           |                             |
|-----------|-----------------------------|
| Packaging | Shrink wrapped & Palletised |
|-----------|-----------------------------|

## TECHNICAL INFORMATION

|                                 |                             |
|---------------------------------|-----------------------------|
| Brick Dimensions (L x W x H)    | 215 x 102.5 x 65mm          |
| Size Tolerances Mean & Range    | T1, R1                      |
| Configuration                   | Frogged                     |
| Voids                           | <20%                        |
| Mean Compressive Strength       | 12 N/mm <sup>2</sup>        |
| Active Soluble Salts            | S2                          |
| Water Absorption                | 15%                         |
| Durability                      | F2                          |
| Gross Dry Density               | 1700 Kg/m <sup>3</sup>      |
| Equivalent Thermal Conductivity | 0.69 W/mK                   |
| Initial Rate of Absorption      | 3-8 kg/(m <sup>2</sup> min) |