

## GREY SMOOTH



[www.bespokebrick.com](http://www.bespokebrick.com)

01634 707707

[enquiries@bespokebrick.com](mailto:enquiries@bespokebrick.com)

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: January 2021

## PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

## TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102.5 x 65mm
Size Tolerances Mean & Range	T2, R2
Configuration	Perforated
Voids	37%
Mean Compressive Strength	45 N/mm <sup>2</sup>
Active Soluble Salts	S2
Water Absorption	6%
Durability	F2
Gross Dry Density	1400 Kg/m <sup>3</sup>
Equivalent Thermal Conductivity	0,21 W/mK
Initial Rate of Absorption	0,8 kg/(m <sup>2</sup> min)