# HARRIER




www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent, ME2 4UY



Issue Date: April 2026


## PRODUCT INFORMATION

| | |
|---|---|
| Packaging | Shrink wrapped & Palletised |

## TECHNICAL INFORMATION

| | |
|---|---|
| Reaction to fire | A1 |
| Brick Dimensions (L x W x H) | 215 x 102 x 65mm |
| Size Tolerances Mean & Range | T1, R1 |
| Configuration | Frogged |
| Voids | NPD |
| Mean Compressive Strength | 17.5 N/mm² |
| Active Soluble Salts | S2 |
| Water Absorption | 12% |
| Durability | F2 |
| Gross Dry Density | 1850 Kg/m³ |
| Equivalent Thermal Conductivity | 0.51 W/mk |
| Initial Rate of Absorption | 1.5-4.0 kg/(m²min) |