

MAROON HANDMADE



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent, ME2 4UY

Issue Date: April 2026

PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Reaction to fire	A1
Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R1
Configuration	Frogged
Voids	20%
Mean Compressive Strength	25 N/mm ²
Active Soluble Salts	S2
Water Absorption	14%
Durability	F2
Gross Dry Density	1800 Kg/m ³
Equivalent Thermal Conductivity	0.53 W/mk
Initial Rate of Absorption	1.5-4.0 kg/(m ² min)