

## ATLANTIS 1



[www.bespokebrick.com](http://www.bespokebrick.com)

01634 707707

[enquiries@bespokebrick.com](mailto:enquiries@bespokebrick.com)

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: January 2021

## PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

## TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	288 x 88 x 50mm
Size Tolerances Mean & Range	T1, R2
Configuration	Perforated
Voids	<35%
Mean Compressive Strength	≥30 N/mm <sup>2</sup>
Active Soluble Salts	S2
Water Absorption	≤12%
Durability	F2
Gross Dry Density	1375 Kg/m <sup>3</sup>
Equivalent Thermal Conductivity	0,44 W/mK
Initial Rate of Absorption	1.5 < IW ≤ 4.0 /(m <sup>2</sup> min)