

ATLANTIS 3



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: January 2021

PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	288 x 88 x 50mm
Size Tolerances Mean & Range	T1, R2
Configuration	Perforated
Voids	<35%
Mean Compressive Strength	≥30 N/mm ²
Active Soluble Salts	S2
Water Absorption	≤8%
Durability	F2
Gross Dry Density	1425 Kg/m ³
Equivalent Thermal Conductivity	0,44 W/mK
Initial Rate of Absorption	0.5 < IW ≤ 1.5 /(m ² min)