

WHITE SMOOTH



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: January 2021

PRODUCT INFORMATION

| | |
|-----------|-----------------------------|
| Packaging | Shrink wrapped & Palletised |
|-----------|-----------------------------|

TECHNICAL INFORMATION

| | |
|---------------------------------|-----------------------------|
| Brick Dimensions (L x W x H) | 215 x 102.5 x 65mm |
| Size Tolerances Mean & Range | T2, R2 |
| Configuration | Perforated |
| Voids | ≤37% |
| Mean Compressive Strength | 45 N/mm ² |
| Active Soluble Salts | S2 |
| Water Absorption | ≤6% |
| Durability | F2 |
| Gross Dry Density | 1350 Kg/m ³ |
| Equivalent Thermal Conductivity | 0,21 W/mK |
| Initial Rate of Absorption | 0.8 kg/(m ² min) |