


RAGLAN



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent,

ME2 4UY

Issue Date: February 2022

PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R2
Configuration	Perforated
Voids	≤ 37%
Mean Compressive Strength	35 N/mm ²
Active Soluble Salts	S0
Water Absorption	≤ 8%
Durability	F2
Gross Dry Density	1400 Kg/m ³
Equivalent Thermal Conductivity	0,35 W/ mK
Initial Rate of Absorption	≤ 0,5 Kg/(m ² ·min)