

RIVENDELL



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent, ME2 4UY

Issue Date: 22nd Dec 2025

PRODUCT INFORMATION

Packaging	Shrink wrapped & Palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Reaction to Fire	A1
Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R2
Configuration	Perforated
Voids	N/A
Mean Compressive Strength	50 N/mm ²
Active Soluble Salts	S2
Water Absorption	≤10%
Durability	F2
Gross Dry Density	1260 Kg/m ³
Thermal Conductivity	0.38 W/mk
Initial Rate of Absorption	≤ 0.6 kg/(m ² min)