

SILVERSTONE TUMBLED



www.bespokebrick.com

01634 707707

enquiries@bespokebrick.com

Unit 1 Magazine B, Ordnance Yard, Upnor Road, Lower Upnor, Kent, ME2 4UY

Issue Date: January 2020

PRODUCT INFORMATION

Packaging	Shrink wrapped & palletised
-----------	-----------------------------

TECHNICAL INFORMATION

Reaction to fire	A1
Brick Dimensions (L x W x H)	215 x 102 x 65mm
Size Tolerances Mean & Range	T2, R1
Configuration	Frogged
Voids	20%
Mean Compressive Strength	15 N/mm ²
Active Soluble Salts	S2
Water Absorption	18%
Durability	F2
Gross Dry Density	1,500 Kg/m ³
Equivalent Thermal Conductivity	50/50 : 0.45 / 90/90 : 0.48 W/mK
Initial Rate of Absorption	1.5 - 4 kg/(m ² .min)